

Technical data		
Product	Pellets	Cartridge
Base	EVA	EVA
Colours	white, natural	white, natural
Viscosity	200 °C 65.000 mPa.s	200 °C 55.000 mPa.s
Softening point	90 °C (according to Ring & Kugel)	103 °C (according to Ring & Kugel)
Thermal stability	85 °C	90 °C
Resistance to cold	-25 °C (knife test)	-20 °C (knife test)
Ideal application temperature	190 - 210 °C	190 - 210 °C
Density	1.40 g/m ³	1.37 g/m ³
Feed rate	15 - 50 m/min	15 - 50 m/min
Consumption	approx. 250 - 300 g/m ²	approx. 250 - 300 g/m ²
Shelf life (store cool and dry)	12 months	12 months

With this information we want to advise you to the best of our knowledge based on our tests and experience. However, we shall assume no liability for the application results in individual cases due to the large number of applications and the storage and application conditions which lie outside the scope of our influence. This also applies to the use of the non-binding technical and commercial Customer Service we provide. We always recommend that you conduct your own tests. We guarantee the consistent quality of our products. We reserve the right to make technical changes and carry out further development.