




























# WIT INJECTION TECHNOLOGY

		23.1/23.2 23.3/23.4 28.1	23.5 29.2	23.6/23.7 29.1
		Concrete specialist	All-rounder	Long curing time
		WIT-VM 100 Injection Mortar	WIT-VM 250 Injection Mortar	WIT-PE 500 Injection Mortar <sup>2)</sup>
				
		<b>Dynamic + cracked and uncracked concrete</b> (general construction permit)	<b>W-VIZ Dynamic</b> 	
		<b>Cracked and uncracked concrete, option 1</b> (ETA approval)	<b>W-VIZ</b>  <b>W-VIZ-IG</b> 	 
		<b>Uncracked concrete, option 7</b> (ETA approval)		
		<b>REBAR, post-installed connections</b> (ETA, general construction permit)		 
		<b>Masonry: Solid and perforated brick, aerated concrete – only with WIT-VM 200 and WIT-VM 250</b> (general construction permit or ETA)	  	
		<b>Uncracked concrete (without approval)</b>		
		<b>Masonry (without approval)</b>		
<b>Temperature in anchoring base</b>		<b>-5 °C to +40 °C</b>	<b>-10 °C to +40 °C</b>	<b>+5 °C to +40 °C</b>
<b>Curing time at 20 °C (dry anchoring base)</b>		<b>45 min</b>	<b>45 min</b>	<b>10 h</b>
<b>Natural brick without discoloration</b>				<b>X<sup>2)</sup></b>
<b>Styrene-free</b>		<b>X</b>	<b>X</b>	<b>X</b>

<sup>1)</sup> Attention: There will be a noticeable styrene odor if the first section of mortar is injected directly into the drill hole instead of being discarded.

<sup>2)</sup> A test must be carried out on the brick in advance to determine whether the mortar will cause discoloration.